


## Gold Nanoparticles

Diameter (nm)	Peak SPR wavelength (nm)
5	515-520
10	515-520
15	520
20	524
30	526
40	530
50	535
60	540
70	548
80	553
90	564
100	572

### Optical Properties of gold nanoparticles of various sizes



北京百欧泰生物科技有限公司

Tel: 010-5365 2239 Email: info@biotyscience.com

Address: 北京市房山区良乡凯旋大街建设路 18 号